



## TECHNICAL DATA SHEET

<b>Product:</b>	FXPE6007 Quartz Silver
<b>Description:</b>	Metallic Sparkle Silver Effect finish High Flowing smooth finish Bonded Metallic
<b>System Coating</b>	Polyester: exterior use, may be over coated with clear powder lacquer, FXAC5001 Acrylic or FXPE5002 Polyester.
<b>Physical data</b>	
Colour:	Silver
Gloss	Satin
Specific Gravity	1.3
<b>Pre-treatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale.
<b>Health &amp; Safety at Work guidelines</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Curing metal temperature</b>	Recommended batch time/temperature: <b>15 minutes @ 180 °C (Metal Temperature)</b>
<b>Resistance to storage</b>	Approx. 24 months in original packaging's at an ambient temperature of 5 to 25 °C. Powder coatings must be stored in a cool and dry place. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.

**Compatibility with 3rd party powder coatings:** Good

Industrial Powder & Paint Services (Powder FX) decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents IPPS best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). IPPS is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted for any specific use. The user or purchaser should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the user.